


TEST REPORT

REPORT NUMBER
170601007SHF-BP-3

ISSUE DATE
2017/9/6

PAGES
4

DOCUMENT CONTROL NUMBER
LFT-APAC-SHF-OP-10a



Test Report

Issue Date: 2017/9/6

Report No. 170601007SHF-BP-3

SUBJECT: Performance testing
Co-Ex Decking A

Dear Sir,

This test report for represents the results of our evaluation of the above referenced product(s) to the requirements contained in the following standards:

TEST METHODS AND STANDARDS
Refer to the next following Pages.

SAMPLE ID	MODEL	SPECIFICATION
S170601007SHF.002	140×22	/

SAMPLE RECEIEVED: 2017/5/31
TESTED FROM: 2017/6/1 TO 2017/7/10

Test Report

Issue Date: 2017/9/6

Report No. 170601007SHF-BP-3

Test Items, Method and Results:

Test Sample	Test Items	Test Method	Test Results
Co-Ex Decking A	Abrasion Resistance	ASTM D4060-14	Mass loss: 30.0 mg Wear index: 30

Note:

1. Type of Wheel: CS-17
2. Load on each Wheel: 1000 g
3. Revolutions: 1000

Test Report

Issue Date: 2017/9/6

Report No. 170601007SHF-BP-3

APPENDIX: SAMPLE RECEIVED PHOTO

