

MAMMUT

TOWER OAK NATURE D3565

KRONOTEX
FLOORS FOR LIVING

General Product Specification

Test	Characteristics	Test method
Formaldehyde emission	< 0.05 ppm	EN 717-1
Surface stain resistance	Grade 5, no visible changes to surface	EN 438-2, 15
Lightfastness	≥ Level 6 Blue Wool Scale ≥ Level 4 Grey Scale	EN ISO 105-B02 EN 20 105-A02
Resistance to cigarette embers	Grade 4, no visible changes to surface	EN 438-2, 18
Fire resistance	Ignites with difficulty, at least C _{fl} -s1	EN 13501-1
Height difference between connected elements	Average: ≤ 0.10 mm max: ≤ 0.15 mm	EN 13329
Edge straightness (bend)	≤ 0.3 mm/m	EN 13329
Openings between connected elements	Average: ≤ 0.15 mm max: ≤ 0.20 mm	EN 13329
Static indentation	< 0.01 mm - no visible changes, Impression in test with straight steel cylinder of 11,3 mm diameter	EN 433

Strength	Thermal conductivity (W / (m × K))	Overall heat transfer coefficient Thermal resistance ((m ² × K) / W)
12	0.14	0.09

Member of:



Kronotex GmbH & Co. KG, Wittstocker Chaussee 1, D-16909 Heiligengrabe, Germany - SWISS KRONO GROUP
 Telefon +49 33 962/69-0 E-Mail sales.floor@kronotex.de
 Telefax +49 33 962/69-280 www.kronotex.com

Deutsche Bank
 (BLZ 120 700 00) Konto 3 951 951
 SWIFT: DEUT DE BB 160
 IBAN: DE 21 1207 0000 0395 1951 00

Commerzbank Berlin
 (BLZ 100 400 00) Konto 200 141 000
 SWIFT: COBA DE BB XXX
 IBAN: DE 26 1004 0000 0200 1410 00

QM-System is certified to
ISO 9001
QS-3281 HH

Amtsgericht Neuruppin: HRA 1190
 Persönlich haftende Gesellschafterin:
 Kronotex Verwaltungs GmbH

Sitz: Heiligengrabe - Amtsgericht Neuruppin: HRB 7338
 Geschäftsführer: Hendrik Hecht, Uwe Jöst, Ingo Lehnhoff
 USt-IdNr. DE 219 154 092 · Steuer-Nr. 052/157/00595